



## Technical Specifications

EGO 60# Text				
Neutral pH, 90 gsm				
Characteristics	Standards	Values	Units	Tolerances
Grammage	ISO 536	90.0	g/m <sup>2</sup>	± 4
Thickness	ISO 534	122	microns	± 9
Bulk	ISO 534	1.36		
Stiffness Lorentzen	ISO 2493	(angle de 15°)		
Grain Direction		1.70	mNm	*
Cross Grain		1.00	mNm	*
Roughness Bendtsen	ISO 8791-2			
Felt Side		600	mL/min	min 500
Moisture	ISO 287	7.0	%	± 0.5
Opacity	ISO 2471			
Dry		91.5	%	Min 89.5
Tensile Strength	ISO 1924-2			
Seconds Grain Direction		70.0	N/15mm	min 60
% Wet Strength Treatment	ISO3781	11.0	%	*
Cobb (60 sec.)	ISO 535	25.0	g/m <sup>2</sup>	*
Whiteness	ISO 11476	107		*
Color	CIELAB 76	Delta E		< 1.2