



Technical Specifications

ICEBERG 60# Text				
Neutral pH, 90 gsm				
Characteristics	Standards	Values	Units	Tolerances
Grammage	ISO 536	90.0	g/m ²	± 4
Thickness	ISO 534	125	microns	± 9
Bulk	ISO 534	1.39		
Stiffness Lorentzen	ISO 2493	(angle de 15°)		
Grain Direction		1.40	mNm	*
Cross Grain		1.10	mNm	*
Roughness Bendtsen	ISO 8791-2			
Felt Side		850	mL/min	min 750
Moisture	ISO 287	6.5	%	± 0.5
Opacity	ISO 2471			
Dry		92.0	%	*
Wet		78.0	%	*
Tensile Strength	ISO 1924-2			
Seconds Grain Direction		68.0	N/15mm	*
% Wet Strength Treatment	ISO3781	11.0	%	*
Cobb (60 sec.)	ISO 535	25.0	g/m ²	*
Whiteness	ISO 11476	151		*
Color	CIELAB 76	Delta E		< 1.2