



## Technical Specifications

SAVOY 100% COTTON 68# Text				
Neutral pH, 100 gsm				
Characteristics	Standards	Values	Units	Tolerances
Grammage	ISO 536	100.0	g/m <sup>2</sup>	± 5
Thickness	ISO 534	165	microns	± 8
Bulk	ISO 534	1.65		
Stiffness Lorentzen	ISO 2493	(angle de 15°)		
Grain Direction		2.00	mNm	*
Roughness Bendtsen	ISO 8791-2			6.4
Felt Side		1100	mL/min	*
Moisture	ISO 287	6.0	%	± 0.5
Opacity	ISO 2471			
Dry		89.0	%	*
Tensile Strength	ISO 1924-2			
Seconds Grain Direction		50.0	N/15mm	*
% Wet Strength Treatment	ISO3781	11.0	%	*
Cobb (60 sec.)	ISO 535	28.0	g/m <sup>2</sup>	*
Whiteness	ISO 11476	141		*
Color	CIELAB 76	Delta E		< 1.2