



Technical Specifications

CARAT 60# Text				
90 gsm				
Characteristics	Standards	Values	Units	Tolerances
Grammage	ISO 536	90.0	g/m ²	± 5
Thickness	ISO 534	127	microns	± 8
Bulk	ISO 534	1.41		
Stiffness Lorentzen	ISO 2493	(angle de 15°)		
Machine Direction		1.50	mNm	*
Cross Grain		0.80	mNm	*
Roughness Bendtsen	ISO 8791-2			
Felt Side		1800	mL/min	*
Moisture	ISO 287	6.5	%	± 0.5
Opacity	ISO 2471			
Dry		90.0	%	*
Tensile Strength	ISO 1924-2			
Seconds Grain Direction		70.0	N/15mm	*
% Wet Strength Treatment	ISO3781	11.0	%	*
Cobb (60 sec.)	ISO 535	20.0	g/m ²	*
Whiteness	ISO 11476	138		*
Color	CIELAB 76	Delta E		< 1.2